

**PCT**WORLD INTELLECTUAL PROPERTY ORGANIZATION  
International Bureau

## INTERNATIONAL APPLICATION PUBLISHED UNDER THE PATENT COOPERATION TREATY (PCT)

<b>(51) International Patent Classification <sup>7</sup> :</b> <b>C08K 3/34, C08L 1/00, 3/00, 89/00</b>	<b>A1</b>	<b>(11) International Publication Number:</b> <b>WO 00/39207</b> <b>(43) International Publication Date:</b> 6 July 2000 (06.07.00)
<b>(21) International Application Number:</b> PCT/US99/30990 <b>(22) International Filing Date:</b> 28 December 1999 (28.12.99) <b>(30) Priority Data:</b> 60/113,987 28 December 1998 (28.12.98) US <b>(71) Applicant:</b> CRANE PLASTICS COMPANY LIMITED PART- NERSHIP [US/US]; 2141 Fairwood Avenue, Columbus, OH 43216 (US). <b>(72) Inventors:</b> ZEHNER, Burch, E.; 1037 Woodtown Drive, Gahanna, OH 43230 (US). BUHRIS, Bryan, K.; 6823 Clymer Drive, Reynoldsburg, OH 43068 (US). <b>(74) Agents:</b> STANDLEY, Jeffrey, S. et al.; Standley & Gilcrest, Llp, Suite 210, 495 Metro Place South, Dublin, OH 43017 (US).		<b>(81) Designated States:</b> AE, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, CA, CH, CN, CR, CU, CZ, DE, DK, DM, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KR, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, NO, NZ, PL, PT, RO, RU, SD, SE, SG, SI, SK, SL, TJ, TM, TR, TT, UA, UG, UZ, VN, YU, ZA, ZW, ARIPO patent (GH, GM, KE, LS, MW, SD, SL, SZ, TZ, UG, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, CH, CY, DE, DK, ES, FI, FR, GB, GR, IE, IT, LU, MC, NL, PT, SE), OAPI patent (BF, BJ, CF, CG, CI, CM, GA, GN, GW, ML, MR, NE, SN, TD, TG).  <b>Published</b> <i>With international search report.</i>
<b>(54) Title:</b> CELLULOSIC, INORGANIC-FILLED PLASTIC COMPOSITE		
<b>(57) Abstract</b>		
<p>The present invention is a cellulosic, inorganic-filled plastic composite. The composite includes about 30 % to about 70 % by weight of the composite of cellulosic material, about 1 % to about 20 % by weight of the composite of talc, and about 25 % to about 40 % by weight of the composite of polyethylene. An extruded article and a method of making the cellulosic, inorganic-filled plastic composite are also disclosed.</p>		

BEST AVAILABLE COPY

**FOR THE PURPOSES OF INFORMATION ONLY**

Codes used to identify States party to the PCT on the front pages of pamphlets publishing international applications under the PCT.

AL	Albania	ES	Spain	LS	Lesotho	SI	Slovenia
AM	Armenia	FI	Finland	LT	Lithuania	SK	Slovakia
AT	Austria	FR	France	LU	Luxembourg	SN	Senegal
AU	Australia	GA	Gabon	LV	Latvia	SZ	Swaziland
AZ	Azerbaijan	GB	United Kingdom	MC	Monaco	TD	Chad
BA	Bosnia and Herzegovina	GE	Georgia	MD	Republic of Moldova	TG	Togo
BB	Barbados	GH	Ghana	MG	Madagascar	TJ	Tajikistan
BE	Belgium	GN	Guinea	MK	The former Yugoslav Republic of Macedonia	TM	Turkmenistan
BF	Burkina Faso	GR	Greece	ML	Mali	TR	Turkey
BG	Bulgaria	HU	Hungary	MN	Mongolia	TT	Trinidad and Tobago
BJ	Benin	IE	Ireland	MR	Mauritania	UA	Ukraine
BR	Brazil	IL	Israel	MW	Malawi	UG	Uganda
BY	Belarus	IS	Iceland	MX	Mexico	US	United States of America
CA	Canada	IT	Italy	NE	Niger	UZ	Uzbekistan
CF	Central African Republic	JP	Japan	NL	Netherlands	VN	Viet Nam
CG	Congo	KE	Kenya	NO	Norway	YU	Yugoslavia
CH	Switzerland	KG	Kyrgyzstan	NZ	New Zealand	ZW	Zimbabwe
CI	Côte d'Ivoire	KP	Democratic People's Republic of Korea	PL	Poland		
CM	Cameroon	KR	Republic of Korea	PT	Portugal		
CN	China	KZ	Kazakhstan	RO	Romania		
CU	Cuba	LC	Saint Lucia	RU	Russian Federation		
CZ	Czech Republic	LI	Liechtenstein	SD	Sudan		
DE	Germany	LK	Sri Lanka	SE	Sweden		
DK	Denmark	LR	Liberia	SG	Singapore		
EE	Estonia						

**CELLULOSIC, INORGANIC-FILLED PLASTIC COMPOSITE**

This application claims the benefit of U.S. Provisional Application No. 60/113,987, filed December 28, 1998.

**BACKGROUND AND SUMMARY OF THE INVENTION**

The application relates generally to cellulose-reinforced composites and, more particularly,  
5 to a cellulosic, inorganic-filled plastic composite.

There is a very high demand for wood products. Although wood is a renewable resource, it takes many years for trees to mature. Consequently, the supply of wood suitable for use in construction is decreasing. Therefore, there is a need to develop alternatives to the use of wood in construction.

10 Cellulosic materials, such as wood fiber, wood flour, sawdust, rice hulls, peanut shells, and the like, have long been added to thermoplastic compounds to achieve a wood-like composite providing reinforcement, reduced coefficient of expansion, and cost reduction. Process methods have been developed to enable blends containing materials having low bulk density (i.e., powders) and poor flow characteristics to be fed at commercially acceptable rates. Blends of this type can  
15 be extruded through dies of the appropriate configuration to produce building product type shapes previously made from wood. For example, U.S. Patent Nos. 3,908,902, 4,091,153, 4,686,251, 4,708,623, 5,002,713, 5,055,247, 5,087,400, and 5,151,238 relate to processes for producing wood-like composites.

A major limitation of cellulosic fillers is the moisture sensitivity of cellulose fibers. This  
20 moisture sensitivity may require predrying of the cellulose fibers and the maintenance of low

moisture conditions at the time of thermoplastic processing, particularly for cellulose in powder form. In addition, the moisture sensitivity of the cellulose fibers requires the exercise of special care during extrusion to ensure cellulosic encapsulation and/or protection against moisture absorption to avoid moisture deterioration of the cellulosic fibers. Furthermore, the extrusion  
5 process can cause thermal degradation of the cellulose fibers.

In light of these shortcomings, there is a need for a cellulosic composite with improved moisture resistance characteristics. Another need exists for a cellulosic composite that is less susceptible to thermal degradation. A need also exists for an improved cellulosic composite that includes inorganic fillers. Yet another need exists for a cellulosic, inorganic-filled composite that  
10 can be used as a substitute for natural wood, particle board, wafer board, and the like.

The present invention satisfies some or all of these needs. One embodiment of the present invention is a cellulosic, inorganic-filled plastic composite. The composite is comprised of cellulosic material, talc, and polyethylene. More particularly, the cellulosic material accounts for about 30% to about 70% by weight of the composite, the talc is about 1% to about 20% by  
15 weight of the composite, and the polyethylene is about 25% to about 40% by weight of the composite.

The present invention also includes an extruded article that is produced by extruding the aforementioned cellulosic, inorganic-filled plastic composite. The composite used to make the extruded article may include any of the optional or preferred features of the above-described  
20 composite.

Another embodiment of the present invention is a method of extruding a cellulosic, inorganic-filled plastic composite profile. The method comprises introducing a cellulosic,

inorganic-filled plastic composite into an extruder. The composite may possess any of the optional or preferred features of the above-described cellulosic, inorganic-filled plastic composite. The composite is then melted and extruded through a profile die to form a profile. The profile is then cooled to achieve a final net shape.

5 In addition to the novel features and advantages mentioned above, other objects and advantages of the present invention will be readily apparent from the following description of the preferred embodiments.

#### DETAILED DESCRIPTION OF PREFERRED EMBODIMENT(S)

10 The present invention is a cellulosic, inorganic-filled plastic composite. The present invention also includes an extruded article made from the composite as well as a method of extruding the composite to form a profile.

The present invention replaces a portion of the cellulosic material with an inorganic filler. In broadest terms, the present invention includes a cellulosic, inorganic-filled plastic composite comprising about 30% by weight to about 70% by weight of the composite of cellulosic material, 15 about 1% to about 20% by weight of the composite of talc, and about 25% to about 40% by weight of the composite of polyethylene.

20 The cellulosic material is preferably present in an amount in the range from about 40% to about 60% by weight of the composite, and more preferably from about 45% by weight to about 55% by weight. The talc is preferably present in an amount in the range from about 5% to about 15% by weight of the composite. In addition, the polyethylene is preferably high density polyethylene, and it is preferably present in an amount in the range from about 25% to about 35% by weight of the composite. The combination of the at least one cellulosic material and the talc is

preferably present in an amount in the range from about 50% to about 80% by weight of the composite, and more preferably from about 55% by weight to about 65% by weight.

Preferably, the cellulosic material is selected from wood fiber, seed husks, ground rice hulls, newspaper, kenaf, and coconut shells. More preferably, the cellulosic material is wood fiber. It should be recognized that wood fiber is available in different forms. Other specific examples of cellulosic material include sawdust, alfalfa, wheat pulp, wood chips, wood particles, ground wood, wood flour, wood flakes, wood veneers, wood laminates, paper, cardboard, straw, cotton, peanut shells, bagass, plant fibers, bamboo fiber, palm fiber, or any other similar materials. Those skilled in the art should recognize that the cellulosic material of the present invention may be any suitable combination of different types of cellulosic material.

One preferred composite is comprised of about 50% to about 55% by weight of the composite of wood fiber, about 5% to about 10% by weight of the composite of talc, and about 30% to about 40% by weight of the composite of high density polyethylene. Another preferred composite is comprised of about 50% to about 55% by weight of the composite of wood fiber, about 10% to about 15% by weight of the composite of talc, and about 25% to about 30% by weight of the composite of high density polyethylene.

The invention also includes an extruded article produced by extruding the cellulosic, inorganic-filled plastic composite. The invention also includes a method of extruding the composite to form a profile. The method comprises introducing the composite as described above into an extruder, melting the composite, extruding the composite through a profile die to form a profile, and cooling the profile.

The following charts help to illustrate the optional and preferred features of the composite of the present invention.

<u>Ingredient</u>	<u>Range (by weight)</u>	<u>Preferred Range (by weight)</u>	<u>Most Preferred Range (by weight)</u>
Cellulosic Material	30 - 70 %	40 - 60%	45 - 55%
Talc	1 - 20%	5 - 15%	
Polyethylene	25 - 40%	25 - 35%	
Combination of Cellulosic Material and Talc	50 - 80%	55 - 65%	

Two preferred composites are:

<u>Ingredient</u>	<u>Amount (by weight)</u>	<u>Amount (by weight)</u>
Wood fiber	50 - 55%	50 - 55%
Talc	5 - 10%	10 - 15%
High Density Polyethylene	30 - 40%	25 - 30%
Additives	0 - 10%	0 - 10%

5

As indicated above, the composite of the present invention may include additives. Examples of additives include lubricants, process aids, cross-linking agents, accelerators, inhibitors, enhancers, compatibilizers, stabilizers, blowing agents, foaming agents, and other additives known in the art. Common commercial lubricants known in the plastics processing industry, both external and internal, can be used. Examples of lubricants which can be used include calcium stearate, zinc stearate, esters, paraffin wax, and amide wax. Examples of cross-linking agents include polyurethanes, such as isocyanates, phenolic resins, unsaturated polyesters, and epoxy resins.

A preferred embodiment of the composite can be made as follows. The wood fiber is preferably dried to between about 0.5% to about 3% in moisture content, and more preferably

15

between about 1% and about 2% moisture by weight. The polyethylene is mixed with the dried wood fiber, talc, stabilizers, lubricants, and process aids in a low intensity mixer such as a ribbon blender. The mixture is preferably melted and processed in a conical, twin screw, counter-rotating extruder with a vent (for example, a Model CM80 extruder by Cincinnati Milacron). A  
5 force feed hopper (i.e., a crammer) is preferred to feed the mixture into the extruder, although other types of hoppers (e.g., a gravity feed hopper) may be used. A vacuum is preferably applied to the vent to further reduce the moisture in the extrudate. The extruder preferably forces the composite through a die or die system to obtain a final profile shape.

The operating temperatures for the first two stages of the extruder may be about 380° F,  
10 while the last two stages, which are located after the vent, may be about 350° F. The die temperature is preferably about 350° F, and the screw temperature is preferably about 360° F. Nevertheless, those skilled in the art should recognize that the temperatures of the extruder and the die may be varied to obtain optimum results for a particular extrusion.

The die design is preferably streamlined with a compaction ratio of between about 2:1 to  
15 about 4:1. It is preferred that the die system includes an extended die land. The extended die land preferably provides the necessary back pressure to obtain a uniform melt, as well as compaction and shaping of the melt.

The resultant product has an appearance similar to wood and may be sawed, sanded, shaped, turned, fastened and/or finished in the same manner as natural wood. The resultant  
20 product is resistant to rot and decay as well as termite attack. The resultant product may be used, for example, as decorative moldings inside or outside of a house, picture frames, furniture, porch decks, window moldings, window components, door components, roofing systems, and any other



type of use where structural requirements do not exceed the physical properties of the resultant material.

Composites made according to the present invention offer several advantages over composites filled only with cellulosic material. For example, composites of the present invention show higher compound bulk density, higher extrusion rates, and less sensitivity to porosity. The composites of the present invention also show reduced moisture sensitivity in the extruded shape as well as reduced smoke and flame spread. In addition, the inorganic filler is readily available, and it has easily defined properties. Moreover, the inorganic filler typically does not require special drying, maintenance, or processing conditions.

The preferred embodiments herein disclosed are not intended to be exhaustive or to unnecessarily limit the scope of the invention. The preferred embodiments were chosen and described in order to explain the principles of the present invention so that others skilled in the art may practice the invention. Having shown and described preferred embodiments of the present invention, those skilled in the art will realize that many variations and modifications may be made to affect the described invention. Many of those variations and modifications will provide the same result and fall within the spirit of the claimed invention. It is the intention, therefore, to limit the invention only as indicated by the scope of the claims.

## WHAT IS CLAIMED IS:

1. A cellulosic, inorganic-filled plastic composite comprising:  
about 30% to about 70% by weight of the composite of cellulosic material;  
about 1% to about 20% by weight of the composite of talc; and  
5 about 25% to about 40% by weight of the composite of polyethylene.
2. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the cellulosic material is present in an amount in the range from about 40% to about 60% by weight of the composite.
3. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the  
10 cellulosic material is present in an amount in the range from about 45% to about 55% by weight of the composite.
4. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the talc is present in an amount in the range from about 5% to about 15% by weight of the composite.
5. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the  
15 polyethylene is present in an amount in the range from about 25% to about 35% by weight of the composite.
6. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the combination of the cellulosic material and the talc is present in an amount in the range from about 50% to about 80% by weight of the composite.
- 20 7. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the combination of the cellulosic material and the talc is present in an amount in the range from about 55% to about 65% by weight of the composite.

8. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the cellulosic material is selected from wood fiber, seed husks, ground rice hulls, newspaper, kenaf, and coconut shells.

9. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the polyethylene is high density polyethylene.

10. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the cellulosic material is wood fiber present in an amount in the range from about 50% to about 55% by weight of the composite, wherein the talc is present in an amount in the range from about 5% to about 10% by weight of the composite, and wherein the polyethylene is high density polyethylene present in an amount in the range from about 30% to about 40% by weight of the composite.

11. The cellulosic, inorganic-filled plastic composite according to claim 1, wherein the cellulosic material is wood fiber present in an amount in the range from about 50% to about 55% by weight of the composite, wherein the talc is present in an amount in the range from about 10% to about 15% by weight of the composite, and wherein the polyethylene is high density polyethylene present in an amount in the range from about 25% to about 30% by weight of the composite.

12. An extruded article, said article produced by extruding a cellulosic, inorganic-filled plastic composite, the composite comprising:

about 30% to about 70% by weight of the composite of cellulosic material;

about 1% to about 20% by weight of the composite of talc; and

about 25% to about 40% by weight of the composite of polyethylene.

13. An extruded article according to claim 12, wherein the cellulosic material is present in an amount in the range from about 40% to about 60% by weight of the composite.
14. An extruded article according to claim 12, wherein the cellulosic material is present in an amount in the range from about 45% to about 55% by weight of the composite.
- 5 15. An extruded article according to claim 12, wherein the talc is present in an amount in the range from about 5% to about 15% by weight of the composite.
16. An extruded article according to claim 12, wherein the polyethylene is present in an amount in the range from about 25% to about 35% by weight of the composite.
17. An extruded article according to claim 12, wherein the combination of the cellulosic  
10 material and the talc is present in an amount in the range from about 50% to about 80% by weight of the composite.
18. An extruded article according to claim 12, wherein the combination of the cellulosic material and the talc is present in an amount in the range from about 55% to about 65% by weight of the composite.
- 15 19. An extruded article according to claim 12, wherein the at least one cellulosic material is selected from wood fiber, seed husks, ground rice hulls, newspaper, kenaf, and coconut shells.
20. An extruded article according to claim 12, wherein the polyethylene is high density polyethylene.
21. An extruded article according to claim 12, wherein the cellulosic material is wood fiber  
20 present in an amount in the range from about 50% to about 55% by weight of the composite, wherein the talc is present in an amount in the range from about 5% to about 10% by weight of

the composite, and wherein the polyethylene is high density polyethylene present in an amount in the range from about 30% to about 40% by weight of the composite.

22. An extruded article according to claim 12, wherein the cellulosic material is wood fiber present in an amount in the range of from about 50% to about 55% by weight of the composite,

5 wherein the talc is present in an amount in the range from about 10% to about 15% by weight of the composite, and wherein the polyethylene is high density polyethylene present in an amount in the range from about 25% to about 30% by weight of the composite.

23. A method of extruding a cellulosic, inorganic-filled plastic composite profile, the method comprising:

10 introducing a cellulosic, inorganic-filled plastic composite into an extruder, the cellulosic, inorganic-filled plastic composite comprising:

about 30% to about 70% by weight of the composite of cellulosic material;

about 1% to about 20% by weight of the composite of talc; and

about 25% to about 40% by weight of the composite of polyethylene.

15 melting the cellulosic, inorganic-filled plastic composite;

extruding the melted cellulosic, inorganic-filled plastic composite through a profile die to form a profile; and

cooling the profile.

24. A method according to claim 23, wherein the cellulosic material is present in an amount in  
20 the range from about 40% to about 60% by weight of the composite.

25. A method according to claim 23, wherein the cellulosic material is present in an amount in the range from about 45% to about 55% by weight of the composite.

26. A method according to claim 23, wherein the talc is present in an amount in the range from about 5% to about 15% by weight of the composite.
27. A method according to claim 23, wherein the polyethylene is present in an amount in the range from about 25% to about 35% by weight of the composite.
- 5 28. A method according to claim 23, wherein the combination of the cellulosic material and the talc is present in an amount in the range from about 50% to about 80% by weight of the composite.
29. A method according to claim 23, wherein the combination of the cellulosic material and the talc is present in an amount in the range from about 55% to about 65% by weight of the  
10 composite.
30. A method according to claim 23, wherein the cellulosic material is selected from wood fiber, seed husks, ground rice hulls, newspaper, kenaf, and coconut shells.
31. A method according to claim 23, wherein the polyethylene is high density polyethylene.
32. A method according to claim 23, wherein the cellulosic material is wood fiber present in  
15 an amount in the range from about 50% to about 55% by weight of the composite, wherein the talc is present in an amount in the range from about 5% to about 10% by weight of the composite, and wherein the polyethylene is high density polyethylene present in an amount in the range from about 30% to about 40% by weight of the composite.
33. A method according to claim 23, wherein the cellulosic material is wood fiber present in  
20 an amount in the range of from about 50% to about 55% by weight of the composite, wherein the talc is present in an amount in the range from about 10% to about 15% by weight of the

composite, and wherein the polyethylene is high density polyethylene present in an amount in the range from about 25% to about 30% by weight of the composite.

# INTERNATIONAL SEARCH REPORT

International application No.  
PCT/US99/30990

## A. CLASSIFICATION OF SUBJECT MATTER

IPC(7) : C08K 3/34; C08L 1/00, 3/00, 89/00

US CL : 524/35, 47, 451

According to International Patent Classification (IPC) or to both national classification and IPC

## B. FIELDS SEARCHED

Minimum documentation searched (classification system followed by classification symbols)

U.S. : 524/35, 47, 451

Documentation searched other than minimum documentation to the extent that such documents are included in the fields searched

Electronic data base consulted during the international search (name of data base and, where practicable, search terms used)  
WEST 1.2

## C. DOCUMENTS CONSIDERED TO BE RELEVANT

Category*	Citation of document, with indication, where appropriate, of the relevant passages	Relevant to claim No.
A	US, 4,323,625 A (CORAN et al) 06 April 1982, entire document.	1-11
A	US, 4,687,793 A (MOTEGI et al) 18 August 1987, entire document.	1-11
Y	US, 5,458,834 A (FABER et al) 17 October 1995, entire document.	1-33
Y	US, 4,783,493 A (MOTEGI et al) 08 November 1988, entire document.	1-33

☐ Further documents are listed in the continuation of Box C. ☐ See patent family annex.

* Special categories of cited documents:	*T* later document published after the international filing date or priority date and not in conflict with the application but cited to understand the principle or theory underlying the invention
*A* document defining the general state of the art which is not considered to be of particular relevance	*X* document of particular relevance; the claimed invention cannot be considered novel or cannot be considered to involve an inventive step when the document is taken alone
*E* earlier document published on or after the international filing date	*Y* document of particular relevance; the claimed invention cannot be considered to involve an inventive step when the document is combined with one or more other such documents, such combination being obvious to a person skilled in the art
*L* document which may throw doubts on priority claim(s) or which is cited to establish the publication date of another citation or other special reason (as specified)	*A* document member of the same patent family
*O* document referring to an oral disclosure, use, exhibition or other means	
*P* document published prior to the international filing date but later than the priority date claimed	

Date of the actual completion of the international search

06 APRIL 2000

Date of mailing of the international search report

18 APR 2000

Name and mailing address of the ISA/US  
Commissioner of Patents and Trademarks  
Box PCT  
Washington, D.C. 20231

Facsimile No. (703) 305-3230

Authorized officer

U. K. RAJGURU

Telephone No. (703) 308-0661



**This Page is Inserted by IFW Indexing and Scanning  
Operations and is not part of the Official Record**

**BEST AVAILABLE IMAGES**

Defective images within this document are accurate representations of the original documents submitted by the applicant.

Defects in the images include but are not limited to the items checked:

- ☐ **BLACK BORDERS**
- ☐ **IMAGE CUT OFF AT TOP, BOTTOM OR SIDES**
- ☐ **FADED TEXT OR DRAWING**
- ☐ **BLURRED OR ILLEGIBLE TEXT OR DRAWING**
- ☐ **SKEWED/SLANTED IMAGES**
- ☐ **COLOR OR BLACK AND WHITE PHOTOGRAPHS**
- ☐ **GRAY SCALE DOCUMENTS**
- ☐ **LINES OR MARKS ON ORIGINAL DOCUMENT**
- ☒ **REFERENCE(S) OR EXHIBIT(S) SUBMITTED ARE POOR QUALITY**
- ☐ **OTHER: \_\_\_\_\_**

**IMAGES ARE BEST AVAILABLE COPY.**

**As rescanning these documents will not correct the image problems checked, please do not report these problems to the IFW Image Problem Mailbox.**